# **KEP 570F**



### **Ethylene Propylene Diene Terpolymer**

## **KUMHO POLYCHEM**

#### **Product Data Sheet**

Features
<ul><li> High loadability</li><li> Excellent extrudability</li></ul>

Test items	Sale Specifications	Unit	Test Method(gauge)
Volatile Matter	Max 1.00	wt %	ASTM D5668
Mooney Viscosity ML(1+4)@125 ℃	59.0 ± 6.0	MU	ASTM D1646
Ethylene Contents	70.0 ± 3.0	wt %	ASTM D3900
ENB Contents	4.5 ± 1.0	wt %	ASTM D6047

#### **Other Products Features**

<b>Product Form</b>	Bale
Packaging	25 kg/Bale in Carton/Mesh Box, LDPE/EOM film, 750 kg(25 kg × 30), 600 kg(25 kg × 24, Pad)
Shelf Life	24 months from date of production at room temperature in dry condition, exposure to light has to be avoided
The Others	RoHS Free

#### **Contact Information**

Head Office	8F, East Wing, Signature	Tower, #100 Cheonggyecheon-ro,	
		00 0 0001 0000	

Jung-gu, Seoul, Korea 82-2-6961-0000

**Plant** 613 Sandanjungang-ro, Yeosu, Jeonnam, Korea

82-61-688-2822

**Revision Date** 05/01/2016

Revision No. 11