

Innoprene™ 2400BH

Thermoplastic Rubber

Product Description

Innoprene™ 2400BH is thermoplastic rubber which incorporates the elasticity of thermoset rubber with the plasticity of thermoplastics. This grade can be formed by blow molding, injection molding and extrusion for various applications such as ducts, boots, bellows, plugs, bumpers and other articles.

General

Applications	Automotive – Boots and Bellows for Steering and Suspension Automotive – Air Induction System Ducts Consumer Applications – Gaskets, Seals Appliance Components		
Color	Black		
Form(s)	Pellets		
Processing	Blow Molding	Injection Molding	Extrusion
Revision Date	2021-04-01		

Physical Properties	Unit	Typical Value	Test Method
Specific Gravity	–	0.93	ISO 1183
Hardness (Shore D, 15 sec.)	–	42	ISO 868
Tensile Strength	Kgf/cm ²	230	ISO 37
Elongation	%	580	ISO 37
Modulus at 100%	Kgf/cm ²	88	ISO 37
Tear Strength	Kgf/cm	75	ISO 34-1
Compression set [125°C, 70 hrs]	%	84	ISO 815

Thermal Property	Unit	Typical Value	Test Method
Brittleness Temperature	°C	-55	ISO 812

Aging Properties [125°C, 168 hrs]	Unit	Typical Value	Test Method
Change in Shore Hardness	–	+2	ISO 188
Change in Tensile Strength	%	+3	ISO 188
Change in Elongation	%	-8	ISO 188

Injection Molding Conditions

Drying Temperature	85 °C
Drying Time	3.0 hrs
Rear Temperature	195 °C
Middle Temperature	195 ~ 205 °C
Front Temperature	210 °C
Nozzle Temperature	215 °C
Processing(Melt) Temperature	210 ~ 215 °C
Mold Temperature	10 ~ 60 °C
Cooling Time	20 ~ 30 sec / 100 ~175 g
Injection Rate	Fast

Extrusion Conditions

Drying Temperature	85 °C
Drying Time	3.0 hrs
Feed Temperature	195 °C
Zone 1 ~ Zone 3 Temperature	195 ~ 205 °C
Head Temperature	210 °C
Die Temperature	215 °C
Processing(Melt) Temperature	210 ~ 215 °C
Screen Pack	20 ~ 60 mesh
Back Pressure	5.0 to 20.0 Mpa

The property values shown are measured on injection molded specimens. They are based on a limited number of tests. Therefore, should not be interpreted as product specifications. These values may shift slightly as additional data are accumulated.

All information supplied by Kumho Polychem in relation to its products is supported by research and believed reliable, however Kumho Polychem assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof.

No liability whatsoever shall attach to Kumho Polychem for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use made of the aforementioned information or products by the buyer.