

Innoprene™ 5430BI

Thermoplastic Elastomer

Product Description

Innoprene™ 5430BI is thermoplastic elastomer which is specifically designed for paintable automotive airbag door covers such as DAB, SAB, PAB and KAB. The product exhibits high melt flow and excellent flexibility at low temperature.

General

Applications	Automotive – Air Bag Door Cover
Color	Black
Form(s)	Pellets
Processing	Injection Molding
Revision Date	2021-04-01

Physical Properties	Unit	Typical Value	Test Method
MFI (230°C, 2.16 Kg)	gram/10 min.	2.1	ASTM D 1238
Density	gram/cm ³	0.89	ASTM D 792
Hardness (Shore D, 15 sec.)	–	40	ASTM D 2240
Tensile Strength @ break	Kgf/cm ²	165	ASTM D 412
Tensile Elongation @ break	%	530	ASTM D 412
Izod Impact @ room Temp.	Kgfc ^m /cm	N.B.	ASTM D 256

The property values shown are measured on injection molded specimens. They are based on a limited number of tests. Therefore, should not be interpreted as product specifications. These values may shift slightly as additional data are accumulated.

All information supplied by Kumho Polychem in relation to its products is supported by research and believed reliable, however Kumho Polychem assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof.

No liability whatsoever shall attach to Kumho Polychem for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use made of the aforementioned information or products by the buyer.