

Product Data Sheet

KUMHO POLYCHEM

Innoprene™ 1830B

Thermoplastic Rubber

Product Description

Innoprene™ 1830B is thermoplastic rubber which incorporates the elasticity of thermoset rubber with the plasticity of thermoplastics. This grade can be formed by injection molding, extrusion and blow molding for various applications such as plugs, bumpers, seals, gaskets and other articles.

General

Applications	Automotive – Air Induction System, Plugs, Bumpers, Seals and Gaskets Industrial – Seals and Gaskets Consumer Applications – Electronics Tubing		
Automotive Spec.	GM GMW 15813 Type 7		
Color	Black		
Form(s)	Pellets		
Processing	Extrusion	Injection Molding	Blow Molding
Revision Date	2021-04-01		

Physical Properties	Unit	Typical Value	Test Method
Specific Gravity	–	0.95	ISO 1183
Hardness (Shore A, 15 sec.)	–	83	ISO 868
Tensile Strength	Kgf/cm ²	102	ISO 37
Elongation	%	592	ISO 37
Modulus at 100%	Kgf/cm ²	42	ISO 37
Tear Strength	Kgf/cm	43	ISO 34-1
Compression set (125°C, 70 hrs)	%	61	ISO 815

Thermal Property	Unit	Typical Value	Test Method
Brittleness Temperature	°C	-59	ISO 812

Aging Properties (150°C, 168 hrs)	Unit	Typical Value	Test Method
Change in Shore Hardness	–	+2	ISO 188
Change in Tensile Strength	%	+13	ISO 188
Change in Elongation	%	+3	ISO 188

Injection Molding Conditions

Drying Temperature	85 °c
Drying Time	3.0 hrs
Rear Temperature	180 °c
Middle Temperature	180 ~ 195 °c
Front Temperature	200 °c
Nozzle Temperature	205 °c
Processing(Melt) Temperature	195 ~ 205 °c
Mold Temperature	10 ~ 60 °c
Cooling Time	20 ~ 30 sec / 100 ~175 g
Injection Rate	Fast

Extrusion Conditions

Drying Temperature	85 °c
Drying Time	3.0 hrs
Feed Temperature	180 °c
Zone 1 ~ Zone 3 Temperature	180 ~ 195 °c
Head Temperature	200 °c
Die Temperature	205 °c
Processing(Melt) Temperature	195 ~ 205 °c
Screen Pack	20 ~ 60 mesh
Back Pressure	5.0 to 20.0 Mpa

The property values shown are measured on injection molded specimens. They are based on a limited number of tests. Therefore, should not be interpreted as product specifications. These values may shift slightly as additional data are accumulated.

All information supplied by Kumho Polychem in relation to its products is supported by research and believed reliable, however Kumho Polychem assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof.

No liability whatsoever shall attach to Kumho Polychem for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use made of the aforementioned information or products by the buyer.